



Standard 2 Flute HSS-Co

Slotting


Hardness	<145 Brinell			<20 HRC			20-30 HRC		
Work Material	Mild Steels Brass Bronze			Medium Tensile Steels Mild Steel Forgings Cast Iron Hard Brass and Bronze Copper			High Tensile Steels Unalloyed Titanium Heat Resistant Ferritic Low Alloys		
Cutting Speed	80-150 SFM			80-110 SFM			50-65 SFM		
Depth of Cut	$a_a=0.5D$								
Mill Dia.	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min
1/64	25,000	0.00002	1.0	23,225	0.00002	0.9	14,000	0.00001	0.3
1/32	14,060	0.00007	2.0	11,610	0.00006	1.4	7,100	0.00005	0.7
3/64	9,370	0.00014	2.6	7,740	0.00012	1.9	4,500	0.00010	0.9
1/16	7,030	0.00020	2.8	5,800	0.00018	2.1	3,550	0.00014	1.0
5/64	5,625	0.00028	3.1	4,645	0.00025	2.3	2,800	0.00020	1.1
3/32	4,685	0.00040	3.7	3,870	0.00035	2.7	2,240	0.00028	1.3
7/64	4,015	0.00047	3.8	3,320	0.00042	2.8	2,000	0.00033	1.3
1/8	3,515	0.00056	3.9	2,900	0.00050	2.9	1,800	0.00040	1.4
9/64	3,125	0.00067	4.2	2,580	0.00060	3.1	1,600	0.00047	1.5
5/32	2,810	0.00080	4.5	2,320	0.00071	3.3	1,400	0.00056	1.6
11/64	2,555	0.00095	4.9	2,110	0.00085	3.6	1,250	0.00067	1.7
3/16	2,340	0.00110	5.2	1,935	0.00100	3.9	1,120	0.00080	1.8
1/4	1,760	0.00160	5.6	1,450	0.00140	4.1	900	0.00112	2.0
5/16	1,400	0.00224	6.3	1,160	0.00200	4.6	710	0.00160	2.3
3/8	1,170	0.00265	6.2	970	0.00236	4.6	630	0.00190	2.4
7/16	1,000	0.00335	6.7	830	0.00300	5.0	500	0.00250	2.5
1/2	880	0.00375	6.6	725	0.00315	4.6	450	0.00265	2.4
9/16	780	0.00400	6.2	645	0.00355	4.6	400	0.00300	2.4
5/8	700	0.00425	6.0	580	0.00375	4.4	355	0.00335	2.4
11/16	640	0.00475	6.1	530	0.00400	4.2	315	0.00355	2.2
3/4	585	0.00475	5.6	485	0.00400	3.9	315	0.00355	2.2
13/16	540	0.00500	5.4	445	0.00400	3.6	280	0.00400	2.2
7/8	500	0.00530	5.3	415	0.00400	3.3	250	0.00400	2.0
15/16	470	0.00560	5.2	390	0.00400	3.1	224	0.00400	1.8
1	440	0.00560	4.9	360	0.00400	2.9	224	0.00400	1.8
1-1/8	390	0.00560	4.4	320	0.00400	2.6	200	0.00400	1.6
1-1/4	350	0.00600	4.2	290	0.00400	2.3	180	0.00400	1.4
1-3/8	320	0.00600	3.8	265	0.00400	2.1	160	0.00400	1.3
1-1/2	295	0.00630	3.7	240	0.00400	1.9	140	0.00400	1.1
1-5/8	270	0.00630	3.4	225	0.00400	1.8	140	0.00400	1.1
1-3/4	250	0.00630	3.2	210	0.00400	1.7	125	0.00400	1.0
1-7/8	235	0.00630	3.0	195	0.00400	1.5	112	0.00400	0.9
2	220	0.00630	2.8	180	0.00400	1.5	112	0.00400	0.9

- 1) Speeds and Feeds for Lists 520, 522, 540, 541, 542, 543, 548, 620 and 641
- 2) Reduce Speeds and Feeds 5-10% for Lists 525, 527, 547
- 3) Reduce Speeds and Feeds 10-20% for Lists 545 and 557
- 4) Increase Speeds and Feeds 5-15% for Lists 530 and 535 (Aluminum only)
- 5) Increase Speeds and Feeds 10-20% for List 529
- 6) Speeds can be increased up to 20% for 520TiN, 522TiN, 540TiN, and 542TiN
- 7) Speeds can be increased up to 15% for Lists 541TiN/TiCN and 548 TiCN





Slotting

Hardness	30-40 HRC			40-50 HRC			-		
Work Material	High Tensile Steels Tool Steels Medium Strength Stainless Steels and Titanium Alloys			Heat Resistant High Strength Stainless Steels and Titanium Alloys			Aluminum Alloy Aluminum Plastics Woods		
Cutting Speed	80-150 SFM			16-32 SFM			150-165 SFM		
Depth of Cut	$a_a=0.5D$ 								
Mill Dia.	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min
1/64	25,000	0.00002	0.8	6,300	0.00001	0.1	25,000	0.00003	1.5
1/32	14,060	0.00004	1.2	3,150	0.00003	0.2	19,250	0.00008	2.9
3/64	9,370	0.00009	1.6	2,000	0.00006	0.2	12,835	0.00014	3.6
1/16	7,030	0.00012	1.7	1,600	0.00008	0.3	9,625	0.00020	3.9
5/64	5,625	0.00017	1.9	1,250	0.00011	0.3	7,700	0.00028	4.3
3/32	4,685	0.00024	2.2	1,000	0.00016	0.3	6,420	0.00038	4.8
7/64	4,015	0.00028	2.2	900	0.00020	0.4	5,500	0.00043	4.7
1/8	3,515	0.00034	2.4	800	0.00024	0.4	4,815	0.00050	4.8
9/64	3,125	0.00040	2.5	710	0.00028	0.4	4,280	0.00060	5.1
5/32	2,810	0.00048	2.7	630	0.00034	0.4	3,850	0.00071	5.5
11/64	2,555	0.00056	2.9	560	0.00040	0.4	3,500	0.00080	5.6
3/16	2,345	0.00067	3.1	500	0.00048	0.5	3,210	0.00095	6.1
1/4	1,760	0.00095	3.3	400	0.00071	0.6	2,400	0.00132	6.4
5/16	1,400	0.00132	3.7	315	0.00100	0.6	1,925	0.00190	7.3
3/8	1,170	0.00160	3.7	280	0.00118	0.7	1,600	0.00212	6.8
7/16	1,000	0.00212	4.3	224	0.00140	0.6	1,375	0.00265	7.3
1/2	880	0.00236	4.1	200	0.00180	0.7	1,200	0.00300	7.2
9/16	780	0.00280	4.4	180	0.00200	0.7	1,070	0.00315	6.7
5/8	700	0.00315	4.4	160	0.00224	0.7	965	0.00335	6.4
11/16	640	0.00355	4.5	140	0.00250	0.7	875	0.00375	6.6
3/4	585	0.00355	4.2	140	0.00250	0.7	800	0.00375	6.0
13/16	540	0.00400	4.3	125	0.00280	0.7	740	0.00400	5.9
7/8	500	0.00400	4.0	112	0.00315	0.7	690	0.00425	5.8
15/16	470	0.00400	3.7	100	0.00355	0.7	640	0.00450	5.8
1	440	0.00400	3.5	100	0.00355	0.7	600	0.00450	5.4
1-1/8	390	0.00400	3.1	90	0.00400	0.7	535	0.00475	5.1
1-1/4	350	0.00400	2.8	80	0.00400	0.6	480	0.00475	4.6
1-3/8	320	0.00400	2.6	71	0.00400	0.6	440	0.00500	4.4
1-1/2	295	0.00400	2.3	63	0.00400	0.5	400	0.00500	4.0
1-5/8	270	0.00400	2.2	63	0.00400	0.5	370	0.00500	3.7
1-3/4	250	0.00400	2.0	56	0.00400	0.4	345	0.00500	3.4
1-7/8	235	0.00400	1.9	50	0.00400	0.4	320	0.00500	3.2
2	220	0.00400	1.8	50	0.00400	0.4	300	0.00500	3.0

1) Based on regular 2FL cutting depth (1/2D) 4FL depth (1/4D) .
 2) In case of deeper operation, slow down feed by 20-50%.

