




Standard 4 Flute and 6 Flute HSS-Co


Side Milling

Hardness	<145 Brinell			<20 HRC			20-30 HRC		
Work Material	Mild Steels Brass Bronze			Medium Tensile Steels Mild Steel Forgings Cast Iron Hard Brass and Bronze Copper			High Tensile Steels Unalloyed Titanium Heat Resistant Ferritic Low Alloys		
Cutting Speed	80-150 SFM			80-110 SFM			16-32 SFM		
Depth of Cut	$a_a = 1.5D$ $a_r = 0.1D$ 								
Mill Dia.	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min
1/16	7,030	0.00020	5.6	5,800	0.00018	4.2	1,465	0.00014	0.8
5/64	5,625	0.00028	6.3	4,645	0.00025	4.6	1,175	0.00020	0.9
3/32	4,685	0.00040	7.5	3,870	0.00036	5.5	980	0.00028	1.1
7/64	4,015	0.00048	7.6	3,320	0.00043	5.6	840	0.00034	1.1
1/8	3,515	0.00056	7.9	2,900	0.00050	5.8	735	0.00040	1.2
9/64	3,125	0.00067	8.4	2,580	0.00060	6.2	650	0.00048	1.2
5/32	2,810	0.00080	9.0	2,320	0.00071	6.6	585	0.00056	1.3
11/64	2,555	0.00095	9.7	2,110	0.00085	7.2	530	0.00067	1.4
3/16	2,340	0.00110	10.3	1,935	0.00100	7.7	490	0.00080	1.6
1/4	1,760	0.00160	11.2	1,450	0.00140	8.1	365	0.00112	1.6
5/16	1,400	0.00224	12.6	1,160	0.00200	9.3	295	0.00160	1.9
3/8	1,170	0.00265	12.4	970	0.00236	9.1	245	0.00190	1.9
7/16	1,000	0.00335	13.5	830	0.00300	10.0	210	0.00250	2.1
1/2	880	0.00375	13.2	725	0.00315	9.1	185	0.00265	1.9
9/16	780	0.00400	12.5	645	0.00355	9.2	160	0.00300	2.0
5/8	700	0.00425	11.9	580	0.00375	8.7	145	0.00335	2.0
11/16	640	0.00475	12.1	530	0.00375	7.9	135	0.00355	1.9
3/4	585	0.00475	11.1	485	0.00375	7.3	120	0.00355	1.7
13/16	540	0.00500	10.8	445	0.00375	6.7	110	0.00400	1.8
7/8	500	0.00530	10.6	415	0.00375	6.2	105	0.00400	1.7
15/16	470	0.00560	10.5	390	0.00375	5.8	100	0.00400	1.6
1	440	0.00560	9.8	365	0.00375	5.4	90	0.00400	1.5
1-1/8	390	0.00560	8.7	320	0.00375	4.8	80	0.00400	1.3
1-1/4	350	0.00600	8.4	290	0.00375	4.4	75	0.00400	1.2
1-3/8	320	0.00600	7.7	265	0.00375	4.0	65	0.00400	1.1
1-1/2	295	0.00630	7.4	240	0.00375	3.6	60	0.00400	1.0
1-3/4	250	0.00630	9.5	210	0.00375	4.7	50	0.00400	1.3
2	220	0.00630	8.3	180	0.00375	4.1	45	0.00400	1.1

- 1) Speeds and Feeds for Lists 540, 541, 542, 543, 547, 548, 575, and 641
- 2) Reduce Speeds and Feeds 15-20% for Lists 557
- 3) Reduce Speeds and Feeds 10-15% for Lists 545, 546, 558 and 646
- 4) Increase Speeds and Feeds 5-15% for Lists 549

Standard 4 Flute and 6 Flute HSS-Co: (Continued)

Side Milling

Hardness	30-40 HRC			40-50 HRC			-		
Work Material	High Tensile Steels Tool Steels Medium Strength Stainless Steels and Titanium Alloys			Heat Resistant High Strength Stainless Steels and Titanium Alloys			Aluminum Alloyed Aluminum Plastics Woods		
Cutting Speed	30-50 SFM			16-32 SFM			150-390 SFM		
Depth of Cut	$a_a = 1.5D$ $a_r = 0.1D$ 								
Mill Dia.	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min	Speed RPM	IPT	Feed in/min
1/16	2,500	0.00012	1.2	1,600	0.00008	0.5	16,500	0.00020	13.2
5/64	2,000	0.00017	1.4	1,250	0.00011	0.6	13,200	0.00028	14.8
3/32	1,600	0.00024	1.5	1,000	0.00016	0.6	11,000	0.00038	16.5
7/64	1,400	0.00028	1.6	900	0.00020	0.7	9,430	0.00043	16.0
1/8	1,250	0.00034	1.7	800	0.00024	0.8	8,250	0.00050	16.5
9/64	1,120	0.00040	1.8	710	0.00028	0.8	7,335	0.00060	17.6
5/32	1,000	0.00048	1.9	630	0.00034	0.8	6,600	0.00071	18.7
11/64	900	0.00056	2.0	560	0.00040	0.9	6,000	0.00080	19.2
3/16	800	0.00067	2.1	500	0.00048	1.0	5,500	0.00095	20.9
1/4	630	0.00095	2.4	400	0.00071	1.1	4,125	0.00132	21.8
5/16	500	0.00132	2.6	315	0.00100	1.3	3,300	0.00190	25.1
3/8	450	0.00160	2.9	280	0.00118	1.3	2,750	0.00212	23.3
7/16	355	0.00212	3.0	224	0.00140	1.3	2,360	0.00265	25.0
1/2	315	0.00236	3.0	200	0.00180	1.4	2,060	0.00300	24.8
9/16	280	0.00280	3.1	180	0.00200	1.4	1,835	0.00315	23.1
5/8	250	0.00315	3.2	160	0.00224	1.4	1,650	0.00335	22.1
11/16	224	0.00355	3.2	140	0.00250	1.4	1,500	0.00375	22.5
3/4	224	0.00355	3.2	140	0.00250	1.4	1,375	0.00375	20.6
13/16	200	0.00400	3.2	125	0.00280	1.4	1,270	0.00400	20.3
7/8	180	0.00400	2.9	112	0.00315	1.4	1,180	0.00425	20.0
15/16	160	0.00400	2.6	100	0.00355	1.4	1,100	0.00450	19.8
1	160	0.00400	2.6	100	0.00355	1.4	1,030	0.00450	18.6
1-1/8	140	0.00400	2.2	90	0.00400	1.4	915	0.00475	17.4
1-1/4	125	0.00400	2.0	80	0.00400	1.3	825	0.00475	15.7
1-3/8	112	0.00400	1.8	71	0.00400	1.1	750	0.00500	15.0
1-1/2	100	0.00400	1.6	63	0.00400	1.0	690	0.00500	13.8
1-3/4	90	0.00400	2.2	56	0.00400	1.3	590	0.00500	17.7
2	80	0.00400	1.9	50	0.00400	1.2	515	0.00500	15.5

1) Based on regular 4FL end mills. cutting depth (1.5D) x cutting width (0.1D)

2) For finish cut, increase RPM 30-50%.