




# Standard Ball Nose Carbide 4 Flute and Multiple Flute

## Profiling (Fractional)

Hardness	-		-		<20 HRC		20-30 HRC		30-40 HRC		40-50 HRC	
Work Material	Aluminum		Cast Iron		Mild Carbon Steels Mild Steels		Pre-hardened Steels Die & Alloy Steels		Pre-hardened Steels Die & Alloy Steels		Hardened Steels	
Cutting Speed	330 SFM		100-115 SFM		100-130 SFM		65-100 SFM		65-82 SFM		43 SFM	
Depth of Cut	$a_a=0.1D$ $a_r=0.2D$ 											
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
3/64	25,000	8.2	8,755	4.0	9,365	3.7	6,720	2.1	5,985	1.2	3,500	1.1
5/64	16,120	10.6	5,250	4.7	5,620	4.4	4,030	2.5	3,590	1.5	2,100	1.3
1/8	10,075	10.6	3,280	4.9	3,510	4.7	2,520	2.7	2,245	1.8	1,315	1.5
5/32	8,060	10.6	2,625	5.2	2,810	5.0	2,015	2.8	1,795	1.9	1,050	1.6
3/16	6,720	11.0	2,190	5.5	2,340	5.3	1,680	2.9	1,495	2.0	875	1.6
1/4	5,040	10.0	1,640	4.7	1,755	4.6	1,260	2.7	1,120	1.9	655	1.5
5/16	4,030	12.2	1,315	5.2	1,405	5.0	1,010	2.8	900	1.9	525	1.6
13/32	3,100	11.7	1,010	5.1	1,080	4.9	775	2.7	690	1.8	405	1.5
15/32	2,685	12.5	875	5.2	935	5.0	670	2.8	600	1.9	350	1.6
5/8	2,015	12.2	655	5.1	700	5.0	505	2.8	450	1.9	265	1.6
25/32	1,610	12.2	525	5.2	560	5.0	405	2.8	360	1.9	210	1.6
1	1,260	12.7	410	5.0	440	4.9	315	2.8	280	1.9	165	1.5

1. Increase speeds & feeds 5-10% for Series 412BN, 414BN, 442BN and 444BN.
2. Reduce speeds & feeds 20-30% for Series 462BN and 464BN.
3. Reduce speeds & feeds 40-50% for Series 482BN and 484BN.
4. Increase speeds & feeds 20-30% for Series 402BN TiN and 404BN TiN.
5. Column for Hardened Steels (40-50 HRC) is for 402BN TiN and 404BN TiN only.

ABOUT OSG

DRILLING

THREADING


MILLING

HOLDERS

INDEX



**Profiling (Metric)**

Hardness	-		-		<20 HRC		20-30 HRC		30-40 HRC		40-50 HRC	
Work Material	Aluminum		Cast Iron		Mild Carbon Steels Mild Steels		Pre-hardened Steels Die & Alloy Steels		Pre-hardened Steels Die & Alloy Steels		Hardened Steels	
Cutting Speed	330 SFM		100-115 SFM		100-130 SFM		65-100 SFM		65-82 SFM		43 SFM	
Depth of Cut	$\Delta a=0.1D$ $\Delta r=0.2D$ 											
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1	25,000	7.0	10,420	4.7	11,150	4.5	8,000	2.5	7,125	1.5	4,170	1.3
2	15,995	8.9	5,210	4.6	5,575	4.4	4,000	2.5	3,565	1.5	2,085	1.3
3	10,665	9.5	3,475	5.2	3,715	5.0	2,665	2.8	2,375	1.9	1,390	1.6
4	8,000	8.9	2,605	5.1	2,785	4.9	2,000	2.8	1,780	1.8	1,040	1.6
5	6,400	8.9	2,085	5.2	2,230	5.0	1,600	2.8	1,425	1.8	835	1.6
6	5,330	8.9	1,735	5.0	1,860	4.9	1,335	2.8	1,190	2.0	695	1.6
8	4,000	12.1	1,305	5.1	1,395	4.9	1,000	2.8	890	1.8	520	1.6
10	3,200	12.1	1,040	5.2	1,115	5.0	800	2.8	715	1.8	415	1.6
12	2,665	12.4	870	5.2	930	5.0	665	2.8	595	1.9	345	1.6
16	2,000	12.1	650	5.1	695	4.9	500	2.8	445	1.8	260	1.6
20	1,600	12.1	520	5.1	555	4.9	400	2.8	355	1.8	210	1.6
25	1,280	12.9	415	5.1	445	4.9	320	2.8	285	1.9	165	1.6

1. Increase speeds & feeds 5-10% for Series 412BN, 414BN, 442BN and 444BN.
2. Reduce speeds & feeds 20-30% for Series 462BN and 464BN.
3. Reduce speeds & feeds 40-50% for Series 482BN and 484BN.
4. Increase speeds & feeds 20-30% for Series 402BN TiN and 404BN TiN.
5. Column for Hardened Steels (40-50 HRC) is for 402BN TiN and 404BN TiN only.

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX