

List 1800 - V-Select

General Drilling Operations

Work Material	Low Carbon Steels 1010, 1018		Carbon Steels		Alloy Steels 4140, 4340		Tool Steels D2, H13		Stainless Steel 15-5PH ,17-4PH		Cast Iron		Cast Aluminum	
Drilling Speed	72-132 SFM		52-99 SFM		40-82 SFM		26-52 SFM		45 - 75 SFM		72-131 SFM		164-328 SFM	
Drill Dia.	Speed		Speed		Speed		Speed		Speed		Speed		Speed	
mm	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR
2	4,950	0.002-0.004	3,660	0.002-0.004	2,960	0.002-0.004	1,900	0.002-0.004	2,910	0.002-0.004	4,920	0.003-0.004	12,000	0.005-0.007
3	3,300	0.004-0.005	2,800	0.004-0.005	2,400	0.004-0.005	1,320	0.004-0.005	1,940	0.004-0.005	3,850	0.004-0.006	10,000	0.008-0.011
4	2,470	0.004-0.006	2,100	0.004-0.006	1,800	0.004-0.006	950	0.004-0.006	1,460	0.004-0.006	2,900	0.005-0.007	7,500	0.009-0.015
5	1,980	0.005-0.007	1,600	0.005-0.007	1,400	0.005-0.007	750	0.005-0.007	1,160	0.005-0.007	2,260	0.006-0.009	6,300	0.011-0.016
6	1,650	0.005-0.007	1,320	0.005-0.007	1,180	0.005-0.007	630	0.005-0.007	970	0.005-0.007	1,900	0.007-0.010	5,000	0.013-0.019
8	1,240	0.006-0.009	1,000	0.006-0.009	900	0.006-0.009	480	0.006-0.009	730	0.006-0.009	1,400	0.008-0.012	4,000	0.015-0.021
10	990	0.008-0.011	800	0.008-0.011	710	0.008-0.011	380	0.008-0.011	580	0.008-0.011	1,120	0.010-0.014	3,150	0.018-0.025
12	820	0.009-0.013	670	0.009-0.013	600	0.009-0.013	320	0.009-0.013	490	0.009-0.013	950	0.012-0.017	2,650	0.021-0.030
13	760	0.010-0.014	620	0.010-0.014	550	0.010-0.014	300	0.010-0.014	450	0.010-0.014	880	0.012-0.017	2,450	0.022-0.031