



List 52504 & 78033 - PHOENIX® P4D

Work Material	Tensile Strength - Hardness	Drilling Speed Vc (SFM)	Feed Rate, f (in/rev)								
			Drilling Depth 4D								
			Ø0.472-0.571 (12-14.5mm)	Ø0.591-0.650 (15-16.5mm)	Ø0.669-0.728 (17-18.5mm)	Ø0.748-0.807 (19-20.5mm)	Ø0.827-0.965 (21-24.5mm)	Ø0.984-1.122 (25-28.5mm)	Ø1.142-1.319 (29-33.5mm)	Ø1.339-2.500 (34-63mm)	
P	Mild Steels, Carbon Steels (1010, 1018)	~180 HB	650 (500 - 800)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.0027 (.0015 - .004)	.003 (.0015 - .0047)	.003 (.0015 - .0047)	.004 (.002 - .006)	.004 (.002 - .007)
	Carbon Steels, Alloy Steels (1050, 4140)	~280 HB	500 (330 - 720)	.0027 (.0015 - .004)	.003 (.0015 - .0055)	.003 (.0015 - .0063)	.0035 (.0015 - .007)	.0047 (.0015 - .006)	0.007 (.0024 - .010)	.008 (.003 - .010)	.008 (.003 - .012)
	Die Steels (H13, D2)	~280 HB	330 (260 - 500)	.0024 (.0015 - .003)	.0024 (.0015 - .004)	.0027 (.0015 - .004)	.003 (.0015 - .0047)	.004 (.0015 - .0051)	.0055 (.0024 - .008)	.007 (.003 - .010)	.007 (.003 - .010)
M	Stainless Steels (304, 420)	~250 HB	430 (260 - 600)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.0027 (.0015 - .004)	.003 (.0015 - .004)	.003 (.0015 - .004)	.0051 (.0024 - .008)	.0063 (.003 - .008)	.0063 (.003 - .008)
K	Cast Iron (No. 35 B)	~350 N/mm ²	650 (500 - 920)	.003 (.0015 - .0047)	.003 (.0015 - .0055)	.0035 (.0015 - .0063)	.004 (.0015 - .008)	.0047 (.0015 - .006)	.008 (.0024 - .012)	.008 (.003 - .012)	.008 (.003 - .012)
	Ductile Cast Iron (60-40-18)	~800 N/mm ²	530 (330 - 720)	.003 (.0015 - .003)	.003 (.0015 - .004)	.003 (.0015 - .0047)	.0035 (.0015 - .006)	.0047 (.0015 - .006)	.006 (.0024 - .010)	.007 (.003 - .010)	.007 (.003 - .010)
N	Aluminum Alloys (6061, 7075)	~13% Si	650 (330 - 2600)	.0027 (.0015 - .0047)	.0027 (.0015 - .0047)	.0035 (.0015 - .0047)	.0047 (.0015 - .008)	.0055 (.0015 - .008)	.008 (.0024 - .012)	.008 (.003 - .012)	.008 (.003 - .012)
S	Heat Resistant Alloys (Inconel 718)	-	100 (50 - 160)	.0015 (.0008 - .0024)	.0015 (.0008 - .0024)	.0015 (.0008 - .0024)	.0015 (.0008 - .0024)	.002 (.0015 - .003)	.0027 (.0024 - .004)	.003 (.0024 - .0047)	.003 (.0024 - .0047)
	Titanium Alloy (Ti-6Al-4V)	-	200 (100 - 330)	.002 (.0015 - .003)	.002 (.0015 - .003)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.003 (.0015 - .004)	.004 (.0024 - .008)	.0055 (.003 - .008)	.0055 (.003 - .008)
H	Pre-hardened Steel (P20, Stavax)	40 - 43 Hrc	330 (200 - 400)	.0024 (.0015 - .004)	.0024 (.0015 - .004)	.0024 (.0015 - .004)	.0024 (.0015 - .004)	.003 (.0015 - .0047)	.003 (.0024 - .0047)	.004 (.0024 - .0051)	.004 (.0024 - .0051)
	Die Cast Steels (A2, S7)	43 - 48 Hrc	260 (165 - 330)	.002 (.0015 - .003)	.002 (.0015 - .003)	.002 (.0015 - .003)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.003 (.0015 - .004)	.003 (.0015 - .004)	.003 (.0015 - .004)
	Hardened Steels (D2)	50 - 55 Hrc	200 (130 - 260)	.002 (.0015 - .003)	.002 (.0015 - .003)	.002 (.0015 - .003)	.0024 (.0015 - .003)	.0024 (.0015 - .003)	.003 (.0015 - .004)	.003 (.0015 - .004)	.003 (.0015 - .004)

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX

