



List 52700 - PHOENIX® PAS: Bore

List 78020 - PHOENIX® PAS: Bore

Work Material		Tensile Strength - Hardness	Insert Size		
			SNKU15...		
			Face Milling		
			Milling Speed Vc (SFM)	Feed Per Tooth fz(in/t)	Depth of Cut Aa (in)
P	Mild Steels, Carbon Steels (1010, 1018)	~180 HB	590 (330 - 820)	0.007 (0.006 - 0.014)	0.120
	Carbon Steels, Alloy Steels (1050, 4140)	~280 HB	590 (330 - 820)	0.007 (0.006 - 0.014)	0.120
	Die Steels (H13, D2)	~280 HB	495 (260 - 655)	0.006 (0.004 - 0.012)	0.120
M	Stainless Steels (304, 420)	~250 HB	395 (260 - 590)	0.005 (0.003 - 0.010)	0.120
K	Cast Iron (No. 35 B)	~300 N/mm ²	590 (330 - 1150)	0.008 (0.006 - 0.014)	0.160
	Ductile Cast Iron (60-40-18)	~600 N/mm ²	590 (330 - 885)	0.008 (0.004 - 0.012)	0.120
S	Heat Resistant Alloys (Inconel 718)	-	115 (85 - 200)	0.004 (0.002 - 0.006)	0.040
	Titanium Alloy (Ti-6Al-4V)	-	130 (100 - 400)	0.005 (0.003 - 0.008)	0.060
H	Pre-hardened Steel (P20, Stavax)	40 - 43 HRC	330 (195 - 495)	0.005 (0.003 - 0.008)	0.060
	Die Cast Steels (A2, S7)	43 - 48 HRC	260 (130 - 395)	0.004 (0.002 - 0.006)	0.020
	Hardened Steels (D2)	50 - 55 HRC	195 (130 - 295)	0.003 (0.002 - 0.006)	0.020

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX

