



List 52900 - PHOENIX® PSF: SA/FA

List 78030 - PHOENIX® PSF: ss

List 52901 - PHOENIX® PSF: Bore

List 78130 - PHOENIX® PSF: Bore

Work Material		Tensile Strength - Hardness	Insert Size		
			SD_T09...		
			Face Milling • Side Milling		
			Milling Speed V _c (SFM)	Feed Per Tooth f _z (in/t)	Depth of Cut A _a (in)
P	Mild Steels, Carbon Steels (1010, 1018)	~180 HB	590 (330 - 820)	0.005 (0.002 - 0.008)	0.120
	Carbon Steels, Alloy Steels (1050, 4140)	~280 HB	590 (330 - 820)	0.005 (0.002 - 0.008)	0.120
	Die Steels (H13, D2)	~280 HB	495 (260 - 655)	0.004 (0.002 - 0.007)	0.120
M	Stainless Steels(Dry) (304SS, 420SS)	~250 HB	495 (260 - 655)	0.004 (0.002 - 0.007)	0.080
	Stainless Steels(Wet) (304SS, 420SS)	~250 HB	260 (195 - 395)	0.004 (0.002 - 0.007)	0.080
K	Cast Iron (FC250)	~350 N/mm ²	590 (330 - 1150)	0.005 (0.002 - 0.008)	0.120
	Ductile Cast Iron (60-40-18)	~800 N/mm ²	590 (330 - 885)	0.005 (0.002 - 0.008)	0.120
N	Aluminum Alloys (6061, 7075)	~13% Si	985 (655 - 4920)	0.006 (0.004 - 0.010)	0.120
S	Heat Resistant Alloys (Inconel 718)	-	115 (85 - 195)	0.004 (0.002 - 0.006)	0.060
	Titanium Alloy (Ti-6Al-4V)	-	130 (100 - 395)	0.004 (0.002 - 0.007)	0.060
H	Pre-hardened Steel (P20, Stavax)	40 - 43 HRC	295 (130 - 495)	0.004 (0.003 - 0.008)	0.060
	Die Cast Steels (A2, S7)	43 - 48 HRC	230 (130 - 395)	0.003 (0.002 - 0.006)	0.020
	Hardened Steels (D2)	50 - 55 HRC	165 (130 - 295)	0.002 (0.002 - 0.004)	0.020

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX

