



List 5340 - EXOCARB® MAX-MINI MRS

General Drilling Operations

Work Material	Carbon Steels 1015, 1050		Alloy Steels 4140, 4130		Austenitic Stainless Steels 304, 316		Martensitic, Ferritic Stainless Steels 420, 430, 430F, 440		Precipitation Hardened Stainless Steels 17-4, 15-5	
Drilling Speed	65-260 SFM		65-180 SFM		50-130 SFM		65-165 SFM		50-130 SFM	
Drill Dia. mm	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR
0.5	25,000	0.0003	23,300	0.0003	17,465	0.0002 - 0.0006	22,300	0.0002 - 0.0006	17,465	0.0002 - 0.0006
1.0	15,700	0.0008	11,600	0.0008	8,730	0.0004 - 0.0012	11,150	0.0004 - 0.0012	8,730	0.0004 - 0.0012
1.5	10,000	0.0008 - 0.0016	7,750	0.0008 - 0.0016	5,820	0.0006 - 0.0018	7,440	0.0006 - 0.0018	5,820	0.0006 - 0.0018
2.0	8,000	0.0012 - 0.0019	5,800	0.0012 - 0.0019	4,365	0.0008 - 0.0024	5,580	0.0008 - 0.0024	4,365	0.0008 - 0.0024
2.5	6,400	0.0014 - 0.0025	4,660	0.0014 - 0.0025	3,500	0.0009 - 0.0030	4,460	0.0009 - 0.0030	3,500	0.0009 - 0.0030
3.0	5,500	0.0016 - 0.0028	3,900	0.0016 - 0.0028	2,900	0.0012 - 0.0035	3,720	0.0012 - 0.0035	2,900	0.0012 - 0.0035

General Drilling Operations

Work Material	Aluminum Alloy 6061, 7075		Cast Aluminum		Copper, Copper Alloys C1020, S2600		Special Alloy Steels, Hardened Steels		Titanium 6AL4V	
Drilling Speed	100-260 SFM		100-200 SFM		65-150 SFM		65-120 SFM		30 HRC	
Drill Dia. mm	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR	Speed RPM	Feed IPR
0.5	25,000	0.0006	25,000	0.0003	21,000	0.0003	17,500	0.0003	15,000	0.0002
1.0	16,000	0.0012	14,500	0.0004	10,600	0.0004	8,800	0.0008	7,250	0.0004
1.5	10,000	0.0012 - 0.0031	9,700	0.0005 - 0.0012	7,100	0.0005 - 0.0012	5,850	0.0012 - 0.0019	4,800	0.0005 - 0.0013
2.0	8,000	0.0016 - 0.0040	7,300	0.0006 - 0.0016	5,300	0.0006 - 0.0016	4,400	0.0016 - 0.0024	3,600	0.0012 - 0.0015
2.5	6,400	0.0020 - 0.0049	5,800	0.0007 - 0.0020	4,270	0.0007 - 0.0020	3,500	0.0020 - 0.0030	3,000	0.0014 - 0.0017
3.0	5,300	0.0024 - 0.0059	4,800	0.0009 - 0.0024	3,560	0.0009 - 0.0024	2,900	0.0024 - 0.0035	2,400	0.0016 - 0.0018

1. Please use in a machine with precise spindle rotation. Tight clamping is critical.
2. The indicated feeds and speeds are for drilling with water-soluble fluid.
3. Please use water-soluble high density fluid (less than 20 times dilution).
4. These tables are applicable for less than 3xD deep drilling operations.
When drilling deeper than 3xD, please peck every 0.25-0.5xD accordingly.
5. The run out with a drill in the spindle should be less than 0.0001".
6. OSG's Shrink Fit System is the recommended tool holder for these drills.

For machines that cannot achieve the speeds indicated in the above table, please set rotation as high as possible. Tool life may be decreased.

