



## List 6300 - A Brand AD: 2D List 6310 - A Brand AD: 4D

### General Drilling Operations

Work Material	Carbon Steels, Mild Steels 1010, 1050, 12L14		Alloy Steels 4140, 4130		Stainless Steels 300SS, 400SS, 17-4PH		High Heat Material						
	210-315 SFM		210-315 SFM		100-185 SFM		80-145 SFM		65-100 SFM		50-90 SFM		
Drilling Speed	Speed RPM		Feed IPR		Speed RPM		Feed IPR		Speed RPM		Feed IPR		
	mm	Inch	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	
2	-	12,700	0.002-0.004	12,700	0.002-0.004	6,900	0.002-0.004	5,460	0.002-0.003	4,000	0.001-0.002	3,390	0.001-0.002
3	-	8,470	0.002-0.005	8,470	0.002-0.005	4,610	0.002-0.005	3,640	0.002-0.003	2,670	0.002-0.002	2,260	0.001-0.002
-	1/8	8,000	0.002-0.005	8,000	0.002-0.005	4,350	0.003-0.005	3,440	0.002-0.003	2,520	0.002-0.003	2,140	0.001-0.002
4	-	6,350	0.003-0.006	6,350	0.003-0.006	3,450	0.003-0.006	2,730	0.002-0.004	2,000	0.002-0.003	1,700	0.002-0.002
-	3/16	5,330	0.003-0.006	5,330	0.003-0.006	2,900	0.004-0.007	2,290	0.003-0.005	1,680	0.002-0.004	1,420	0.002-0.003
6	-	4,230	0.005-0.009	4,230	0.005-0.009	2,300	0.005-0.009	1,820	0.004-0.005	1,330	0.004-0.005	1,130	0.002-0.004
-	1/4	4,000	0.005-0.009	4,000	0.005-0.009	2,180	0.005-0.010	1,720	0.004-0.006	1,260	0.004-0.005	1,070	0.002-0.004
8	-	3,170	0.006-0.011	3,170	0.006-0.011	1,730	0.006-0.011	1,360	0.005-0.007	1,000	0.005-0.006	850	0.003-0.005
-	3/8	2,670	0.007-0.012	2,670	0.007-0.012	1,450	0.008-0.012	1,150	0.005-0.008	840	0.006-0.008	710	0.004-0.006
10	-	2,540	0.008-0.012	2,540	0.008-0.012	1,380	0.008-0.012	1,090	0.006-0.009	800	0.006-0.008	680	0.004-0.006
-	7/16	2,290	0.008-0.012	2,290	0.008-0.012	1,240	0.008-0.012	980	0.007-0.010	720	0.007-0.009	610	0.004-0.007
12	-	2,120	0.008-0.012	2,120	0.008-0.012	1,150	0.008-0.012	910	0.007-0.011	670	0.007-0.009	560	0.005-0.007
-	1/2	2,000	0.008-0.012	2,000	0.008-0.012	1,090	0.008-0.012	860	0.008-0.011	630	0.008-0.009	530	0.005-0.008
14	-	1,810	0.009-0.014	1,810	0.009-0.014	990	0.009-0.014	780	0.008-0.013	570	0.008-0.011	480	0.005-0.008
-	5/8	1,600	0.010-0.014	1,600	0.010-0.014	870	0.009-0.014	690	0.009-0.013	500	0.008-0.011	430	0.005-0.008
16	-	1,600	0.010-0.014	1,600	0.010-0.014	870	0.009-0.014	690	0.009-0.013	500	0.008-0.011	430	0.005-0.008
18	-	1,410	0.011-0.015	1,410	0.011-0.015	770	0.011-0.015	610	0.010-0.014	440	0.008-0.011	380	0.005-0.008
-	3/4	1,330	0.012-0.016	1,330	0.012-0.016	720	0.011-0.015	570	0.011-0.015	420	0.008-0.012	360	0.005-0.008
20	-	1,270	0.012-0.016	1,270	0.012-0.016	690	0.012-0.016	550	0.012-0.016	400	0.008-0.012	340	0.005-0.008

### General Drilling Operations

Work Material	Cast Iron		Ductile Cast Iron		Special Alloy Steels, Hardened Steels								
	210-315 SFM		156-265 SFM		155-235 SFM		100-160 SFM		100-130 SFM		65-95 SFM		
Drilling Speed	Speed RPM		Feed IPR		Speed RPM		Feed IPR		Speed RPM		Feed IPR		
	mm	Inch	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	
2	-	12,700	0.002-0.004	10,190	0.002-0.004	9,460	0.002-0.004	6,310	0.002-0.003	5,570	0.002-0.003	3,890	0.001-0.002
3	-	8,470	0.002-0.005	6,790	0.002-0.005	6,310	0.002-0.005	4,210	0.002-0.003	3,720	0.002-0.003	2,590	0.002-0.002
-	1/8	8,000	0.002-0.005	6,420	0.003-0.005	5,960	0.002-0.005	3,980	0.002-0.003	3,510	0.002-0.003	2,450	0.002-0.003
4	-	6,350	0.003-0.006	5,100	0.003-0.006	4,730	0.003-0.006	3,160	0.003-0.004	2,780	0.003-0.004	1,940	0.002-0.003
-	3/16	5,330	0.003-0.006	4,280	0.004-0.007	3,980	0.003-0.006	2,650	0.003-0.005	2,340	0.003-0.005	1,630	0.003-0.004
6	-	4,230	0.005-0.009	3,400	0.005-0.009	3,150	0.005-0.009	2,100	0.005-0.006	1,860	0.005-0.006	1,290	0.004-0.005
-	1/4	4,000	0.005-0.009	3,210	0.006-0.009	2,980	0.005-0.009	1,990	0.005-0.007	1,760	0.005-0.007	1,220	0.004-0.006
8	-	3,170	0.006-0.011	2,550	0.006-0.011	2,360	0.006-0.011	1,580	0.006-0.008	1,390	0.006-0.008	970	0.005-0.007
-	3/8	2,670	0.007-0.012	2,140	0.008-0.012	1,990	0.007-0.012	1,320	0.008-0.009	1,170	0.008-0.009	820	0.006-0.008
10	-	2,540	0.008-0.012	2,040	0.008-0.012	1,890	0.008-0.012	1,260	0.008-0.010	1,110	0.008-0.010	780	0.007-0.009
-	7/16	2,290	0.008-0.012	1,830	0.008-0.012	1,700	0.008-0.012	1,140	0.009-0.011	1,000	0.009-0.011	700	0.007-0.009
12	-	2,120	0.008-0.012	1,700	0.008-0.012	1,580	0.008-0.012	1,050	0.009-0.012	930	0.009-0.012	650	0.007-0.009
-	1/2	2,000	0.008-0.012	1,600	0.008-0.012	1,490	0.008-0.012	990	0.010-0.012	880	0.010-0.012	610	0.008-0.010
14	-	1,810	0.009-0.014	1,460	0.009-0.014	1,350	0.009-0.014	900	0.011-0.014	800	0.011-0.014	550	0.008-0.011
-	5/8	1,600	0.010-0.014	1,280	0.010-0.014	1,190	0.010-0.014	790	0.012-0.015	700	0.012-0.015	490	0.009-0.012
16	-	1,600	0.010-0.014	1,280	0.010-0.014	1,190	0.010-0.014	790	0.012-0.015	700	0.012-0.015	490	0.009-0.012
18	-	1,410	0.011-0.015	1,130	0.011-0.015	1,050	0.011-0.015	700	0.014-0.018	620	0.014-0.018	430	0.010-0.014
-	3/4	1,330	0.012-0.016	1,070	0.012-0.016	990	0.012-0.016	660	0.015-0.019	680	0.015-0.019	410	0.011-0.015
20	-	1,270	0.012-0.016	1,020	0.012-0.016	940	0.012-0.016	630	0.016-0.020	560	0.016-0.020	390	0.012-0.016

#### Note:

- The indicated speeds and feeds are for drilling with **water-soluble oil**.
- Suitable cutting fluid is water-soluble high density oil (less than 20 times dilution).
- When using non-water-soluble oil or water-soluble oil (over 20 times dilution), reduce cutting speed by 30%.
- These conditions are for drilling depth under 3 times the drill diameter.
- For machines that cannot achieve the speeds indicated in the table please set rotation as high as possible. Tool life may be reduced.

