





List 660: Super High-Helix - Regular Length - Multiple Flute

Semi-Roughing Cut

Hardness	<20 HRC		20-30 HRC		30-40 HRC		40-50 HRC	
Work Material	1045 1055 Cast Steel Cast Iron		15-5 PH 4140, 4340, 304, 316, 410, 420, 430 A1		6AL-4V 17-4 PH H13 (HRC38) P20, D2 Beryllium Copper		H13 (HRC45) Inconel 718 Hastelloy Waspaloy	
Cutting Speed	80-100 SFM		50-65 SFM		35-45 SFM		20-30 SFM	
Depth of Cut	$a_a=1.5D$ $a_r=0.3D$ 							
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1/4	1,400	3.0	900	1.9	600	1.2	400	0.7
5/16	1,100	2.8	700	1.8	500	1.3	300	0.7
3/8	900	3.2	600	2.1	400	1.4	250	0.7
7/16	780	3.3	500	2.1	355	1.5	224	0.8
1/2	710	3.8	450	2.4	315	1.7	200	0.8
5/8	560	3.8	350	2.3	250	1.7	160	0.9
3/4	450	3.8	300	2.6	200	1.7	140	0.8
7/8	400	4.0	250	2.5	180	1.8	110	0.8
1	315	3.5	200	2.2	160	1.8	100	0.8

Finish Cut

Hardness	<20 HRC		20-30 HRC		30-40 HRC		40-50 HRC	
Work Material	1045 1055 Cast Steel Cast Iron		15-5 PH 4140, 4340, 304, 316, 410, 420, 430 A1		6AL-4V 17-4 PH H13 (HRC38) P20, D2 Beryllium Copper		H13 (HRC45) Inconel 718 Hastelloy Waspaloy	
Cutting Speed	80-100 SFM		50-65 SFM		35-45 SFM		20-30 SFM	
Depth of Cut	$a_a=1.5D$ $a_r=0.1D$ 							
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1/4	1,400	5.9	900	3.1	600	2.0	400	1.1
5/16	1,100	6.6	700	3.3	500	2.4	315	1.2
3/8	900	6.3	600	3.5	400	2.3	250	1.2
7/16	780	7.0	500	3.7	355	2.7	224	1.4
1/2	710	6.7	450	3.6	315	2.5	200	1.4
5/8	560	6.3	350	3.5	250	2.5	160	1.5
3/4	450	5.1	300	3.2	200	2.1	140	1.5
7/8	400	6.0	250	3.7	180	2.7	110	1.6
1	350	5.3	200	3.0	160	2.4	100	1.4