





List HP418

Profiling Milling (Fractional)

Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC	
Work Material	Cast Iron		Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels	
Cutting Speed	497 SFM		397 SFM		330 SFM		262 SFM		230 SFM		196 SFM		146 SFM	
Depth of Cut	$a_r=0.1D$ $a_r=0.2D$ 										$a_a=0.05D$ $a_r=0.1D$			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
3/32	20,450	37.0	16,520	30.1	13,590	24.5	10,955	15.8	9,625	11.4	8,295	8.3	6,235	5.5
1/8	14,800	37.0	11,975	30.1	10,050	24.8	8,080	16.2	7,075	12.0	6,070	8.7	4,540	5.7
3/16	9,975	40.3	8,050	32.8	6,730	24.9	5,355	17.5	4,710	14.6	4,025	11.1	3,015	6.9
1/4	7,600	43.0	6,070	35.0	5,060	27.2	4,015	18.9	3,530	15.8	3,010	11.8	2,245	7.4
3/8	5,035	48.1	4,025	38.6	3,340	29.7	2,650	20.9	2,330	17.1	2,005	13.1	1,480	8.3

Profiling Milling (Metric)


Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC	
Work Material	Cast Iron		Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels	
Cutting Speed	497 SFM		397 SFM		330 SFM		262 SFM		230 SFM		196 SFM		146 SFM	
Depth of Cut	$a_r=0.1D$ $a_r=0.2D$ 										$a_a=0.05D$ $a_r=0.1D$			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1	25,000	23.5	25,000	23.5	25,000	19.3	2,500	1.6	25,000	12.7	19,050	8.2	14,200	5.5
2	25,000	38.9	19,250	30.1	16,000	24.7	12,700	15.8	11,150	11.3	9,500	8.1	7,100	5.3
3	16,100	40.2	12,850	32.2	10,700	26.4	8,500	16.9	7,450	12.4	6,350	8.9	4,750	6.0
4	12,050	38.3	9,650	30.2	8,000	24.7	6,350	17.2	5,600	14.4	4,750	10.4	3,550	6.7
5	9,650	43.1	7,700	35.0	6,400	26.0	5,100	18.2	4,450	15.0	3,800	11.5	2,850	7.1
6	8,050	45.5	6,400	36.8	5,350	28.6	4,250	20.0	3,700	16.5	3,150	12.4	2,350	7.7
8	6,050	51.2	4,800	41.0	4,000	30.9	3,200	21.8	2,800	17.9	2,400	12.8	1,750	8.1
10	4,850	49.0	3,850	38.7	3,200	30.1	2,550	21.3	2,250	17.8	1,900	13.4	1,400	8.3
12	4,000	45.3	3,200	36.2	2,650	28.6	2,100	20.1	1,850	17.3	1,600	13.0	1,200	8.3






List HP418: (continued)

High Speed Light Milling (Fractional)

Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC										
Work Material	Mild Steels Carbon Steels Cast Iron		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels										
Cutting Speed	980 SFM		850 SFM		740 SFM		590 SFM		590 SFM		410 SFM										
Depth of Cut	$a_a=0.02D$ $a_r=0.05D$ 						<table border="1"> <thead> <tr> <th>Dia</th> <th>a_a</th> <th>a_r</th> </tr> </thead> <tbody> <tr> <td>D≤5/32</td> <td>0.02D</td> <td>0.05D</td> </tr> <tr> <td>5/32<D</td> <td>0.13D</td> <td>0.05D</td> </tr> </tbody> </table>						Dia	a _a	a _r	D≤5/32	0.02D	0.05D	5/32<D	0.13D	0.05D
Dia	a _a	a _r																			
D≤5/32	0.02D	0.05D																			
5/32<D	0.13D	0.05D																			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min									
3/32	25,000	125.3	25,000	126.7	25,000	115.8	24,050	104.2	24,050	99.8	16,700	60.1									
1/8	25,000	170.0	25,000	175.2	22,650	143.3	18,050	107.2	18,050	104.0	12,550	60.1									
3/16	17,350	166.8	17,350	176.0	15,050	119.3	12,050	95.6	12,050	95.2	8,350	50.4									
1/4	13,000	163.6	12,880	161.7	11,050	103.8	9,080	84.8	9,080	84.8	6,305	43.5									
3/8	8,650	107.7	8,660	108.0	7,575	70.7	6,035	56.4	6,035	56.4	4,180	29.6									

High Speed Light Milling (Metric)

Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC										
Work Material	Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels										
Cutting Speed	980 SFM		850 SFM		740 SFM		590 SFM		590 SFM		410 SFM										
Depth of Cut	$a_a=0.02D$ $a_r=0.05D$ 						<table border="1"> <thead> <tr> <th>Dia</th> <th>a_a</th> <th>a_r</th> </tr> </thead> <tbody> <tr> <td>D≤8</td> <td>0.02D</td> <td>0.05D</td> </tr> <tr> <td>8<D</td> <td>0.13D</td> <td>0.05D</td> </tr> </tbody> </table>						Dia	a _a	a _r	D≤8	0.02D	0.05D	8<D	0.13D	0.05D
Dia	a _a	a _r																			
D≤8	0.02D	0.05D																			
8<D	0.13D	0.05D																			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min									
1	25,000	55.1	25,000	55.1	25,000	49.2	25,000	44.6	25,000	44.6	25,000	39.4									
2	25,000	107.8	25,000	108.6	25,000	98.9	25,000	88.0	25,000	88.0	19,900	61.8									
3	25,000	169.7	25,000	174.9	24,000	151.7	19,100	110.1	19,100	110.1	13,250	63.0									
4	20,650	165.9	20,650	177.0	17,950	128.9	14,300	96.2	14,300	96.2	9,950	53.6									
5	16,500	173.6	16,500	179.6	14,350	119.2	11,450	96.4	11,450	96.4	7,950	50.1									
6	13,750	172.8	13,750	172.3	12,000	112.4	9,550	89.0	9,550	89.0	6,650	45.7									
8	10,300	128.6	10,300	129.7	9,000	83.2	7,150	66.7	7,150	66.7	5,000	35.0									
10	8,250	102.5	8,250	102.0	7,200	67.3	5,750	53.5	5,750	53.5	4,000	28.3									
12	6,900	85.4	6,900	85.1	6,000	55.6	4,750	43.6	4,750	43.6	3,300	22.9									

