





List HP421BN, HP441BN

Profiling Milling (Fractional)

Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC	
Work Material	Cast Iron		Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels	
Cutting Speed	575 SFM		460 SFM		375 SFM		310 SFM		260 SFM		230 SFM		165 SFM	
Depth of Cut	$a_a=0.1D$ $a_r=0.2D$ 										$a_a=0.05D$ $a_r=0.1D$			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1/16	25,000	31.3	25,000	30.5	23,000	25.1	19,000	16.9	16,000	11.4	14,000	8.5	10,000	5.3
3/32	23,500	42.6	18,800	34.2	15,300	27.4	12,600	18.2	10,600	12.7	9,400	9.3	6,700	5.7
1/8	17,500	45.3	14,000	36.2	11,600	29.5	9,300	19.3	8,150	14.6	7,000	10.6	5,200	7.1
5/32	14,050	44.1	11,550	35.8	9,700	29.5	7,750	20.5	6,750	16.9	5,800	12.2	4,300	7.9
3/16	11,750	48.0	9,500	39.0	7,900	29.9	6,300	20.9	5,550	17.3	4,700	13.0	3,550	7.9
1/4	8,750	53.1	7,000	42.9	5,800	33.1	4,600	22.8	4,050	19.3	3,450	14.2	2,550	8.7
5/16	7,250	60.6	5,800	48.8	4,800	36.6	3,800	25.6	3,350	20.9	2,850	15.0	2,100	9.4
3/8	5,900	57.1	4,700	45.3	3,900	35.0	3,100	24.4	2,700	20.5	2,350	15.4	1,700	9.4
7/16	4,950	53.1	3,950	42.1	3,300	33.1	2,600	23.2	2,300	19.7	1,950	14.6	1,450	9.1
1/2	4,350	50.4	3,450	40.6	2,900	31.9	2,300	22.4	2,000	18.9	1,700	14.2	1,250	8.7
5/8	3,600	49.6	2,850	39.4	2,350	30.3	1,850	22.4	1,600	17.7	1,400	12.6	1,050	8.7
3/4	3,000	46.1	2,400	36.6	2,000	28.0	1,600	21.7	1,350	17.3	1,200	11.8	900	7.9
1	2,450	37.6	1,760	31.3	1,430	21.5	1,185	16.5	1,000	13.5	880	9.6	630	6.5

Increase feeds 40% to 50% for Series HP441BN.

Profiling Milling (Metric)

Hardness	-		<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC	
Work Material	Cast Iron		Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels	
Cutting Speed	575 SFM		460 SFM		375 SFM		310 SFM		260 SFM		230 SFM		165 SFM	
Depth of Cut	$a_a=0.1D$ $a_r=0.2D$ 										$a_a=0.05D$ $a_r=0.1D$			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1	25,000	23.5	25,000	23.5	25,000	19.3	25,000	15.7	25,000	12.7	25,000	10.8	16,000	6.2
2	25,000	38.9	22,350	34.9	18,200	28.1	15,050	18.7	12,600	12.8	11,150	9.5	8,000	6.0
3	18,600	46.4	14,900	37.4	12,150	29.9	10,050	20.0	8,400	14.0	7,450	10.5	5,350	6.8
4	14,000	44.5	11,150	34.9	9,100	28.1	7,550	20.5	6,300	16.2	5,600	12.2	4,000	7.5
5	11,200	50.1	8,950	40.7	7,300	29.7	6,000	21.5	5,050	17.0	4,450	13.4	3,200	8.0
6	9,300	52.6	7,450	42.9	6,050	32.4	5,000	23.5	4,200	18.7	3,700	14.5	2,650	8.7
8	7,000	59.2	5,600	47.8	4,550	35.2	3,750	25.5	3,150	20.1	2,800	14.9	2,000	9.3
10	5,600	56.5	4,450	44.7	3,650	34.4	3,000	25.1	2,500	19.8	2,250	15.9	1,600	9.5
12	4,650	52.6	3,700	41.9	3,050	32.9	2,500	23.9	2,100	19.6	1,850	15.0	1,350	9.3
14	4,000	48.6	3,200	40.2	2,600	30.7	2,150	22.3	1,800	17.7	1,600	14.0	1,150	8.5
16	3,500	48.6	2,800	39.0	2,300	29.8	1,900	22.7	1,600	17.6	1,400	12.9	1,000	8.0
18	3,100	46.1	2,500	37.1	2,050	28.1	1,650	22.0	1,400	17.4	1,250	12.1	900	7.8
20	2,800	43.3	2,250	35.0	1,800	25.7	1,500	20.8	1,250	16.2	1,100	11.1	800	7.3
22	2,550	42.1	2,050	32.4	1,650	22.5	1,350	18.9	1,150	15.3	1,000	10.4	750	7.5
25	2,250	36.8	1,800	31.7	1,450	21.3	1,200	17.0	1,000	12.9	900	9.6	650	6.5

Increase feeds 40% to 50% for Series HP441BN.

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX


CONTINUED ➔






List HP421BN, HP441BN: (continued)

High Speed Light Milling (Fractional)

Hardness	<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC										
Work Material	Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels										
Cutting Speed	985 SFM		855 SFM		740 SFM		590 SFM		590 SFM		400 SFM										
Depth of Cut	$a_a=0.02D$ $a_r=0.05D$ 						<table border="1"> <thead> <tr> <th>Dia</th> <th>aa</th> <th>ar</th> </tr> </thead> <tbody> <tr> <td>D≤5/32</td> <td>0.02D</td> <td>0.05D</td> </tr> <tr> <td>5/32<D</td> <td>0.13D</td> <td>0.05D</td> </tr> </tbody> </table>						Dia	aa	ar	D≤5/32	0.02D	0.05D	5/32<D	0.13D	0.05D
Dia	aa	ar																			
D≤5/32	0.02D	0.05D																			
5/32<D	0.13D	0.05D																			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min									
1/16	25,000	80.3	25,000	77.6	25,000	69.9	25,000	65.9	25,000	63.4	24,450	54.3									
3/32	25,000	125.5	25,000	127.6	25,000	115.4	24,050	104.4	24,050	99.4	16,300	58.4									
1/8	25,000	174.8	25,000	181.6	22,650	146.5	18,050	110.5	18,050	106.7	12,250	59.7									
5/32	24,100	192.4	20,900	177.8	18,100	129.3	14,450	101.7	14,450	96.7	9,800	52.9									
3/16	20,100	198.9	17,450	180.2	15,100	121.5	12,050	96.5	12,050	96.3	8,150	49.3									
1/4	15,050	189.5	13,100	164.9	11,300	106.1	9,000	83.8	9,000	83.8	6,100	42.0									
5/16	12,050	151.1	10,500	132.4	9,050	83.9	7,250	67.7	7,250	67.7	5,000	35.4									
3/8	10,050	125.1	8,700	108.4	7,400	69.3	5,900	55.1	5,900	55.1	4,100	28.7									
7/16	8,250	102.8	7,450	92.3	6,200	57.9	4,950	45.7	4,950	45.7	3,400	24.0									
1/2	7,250	90.2	6,550	81.3	5,450	50.4	4,300	40.2	4,300	40.2	3,000	20.9									
5/8	6,050	75.6	5,200	63.8	4,500	41.7	3,600	33.9	3,600	33.9	2,450	17.3									
3/4	5,050	62.6	4,350	54.7	3,750	35.4	3,000	28.3	3,000	28.3	2,100	14.6									
1	3,765	46.8	3,270	41.1	2,830	26.7	2,250	21.2	2,250	21.2	1,530	10.6									

Increase feeds 40% to 50% for Series HP441BN.

High Speed Light Milling (Metric)

Hardness	<20 HRC		20-30 HRC		30-38 HRC		38-45 HRC		45-55 HRC		55-60 HRC										
Work Material	Mild Steels Carbon Steels		Alloy Steels Tool Steels Ti Alloys (Annealed)		Hardened Steels Pre-hardened Steels Ti Alloys (Solution Treated and Aged)		Hardened Steels Pre-hardened Steels Stainless Steels Inconel Ni Based Alloys		Hardened Steels		Hardened Steels										
Cutting Speed	985 SFM		855 SFM		740 SFM		590 SFM		590 SFM		400 SFM										
Depth of Cut	$a_a=0.02D$ $a_r=0.05D$ 						<table border="1"> <thead> <tr> <th>Dia</th> <th>aa</th> <th>ar</th> </tr> </thead> <tbody> <tr> <td>D≤4</td> <td>0.02D</td> <td>0.05D</td> </tr> <tr> <td>4<D</td> <td>0.13D</td> <td>0.05D</td> </tr> </tbody> </table>						Dia	aa	ar	D≤4	0.02D	0.05D	4<D	0.13D	0.05D
Dia	aa	ar																			
D≤4	0.02D	0.05D																			
4<D	0.13D	0.05D																			
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min									
1	25,000	55	25,000	55	25,000	49	25,000	47	25,000	47	25,000	39									
2	25,000	108	25,000	109	25,000	99	25,000	93	25,000	93	19,400	60									
3	25,000	170	25,000	175	23,950	151	19,100	113	19,100	113	12,950	62									
4	23,900	192	20,750	178	17,950	129	14,350	102	14,350	102	9,700	53									
5	19,150	202	16,600	181	14,350	119	11,450	96	11,450	96	7,750	49									
6	15,950	201	13,850	174	12,000	113	9,550	89	9,550	89	6,450	44									
8	12,000	150	10,400	131	9,000	83	7,150	67	7,150	67	4,850	34									
10	9,550	119	8,300	103	7,200	67	5,750	54	5,750	54	3,900	28									
12	7,950	99	6,900	85	6,000	56	4,750	44	4,750	44	3,250	23									
14	6,850	85	5,950	73	5,150	48	4,100	39	4,100	39	2,750	19									
16	6,000	75	5,200	64	4,500	42	3,600	34	3,600	34	2,450	17									
18	5,300	65	4,600	58	4,000	38	3,200	30	3,200	30	2,150	15									
20	4,800	60	4,150	52	3,600	34	2,850	27	2,850	27	1,950	14									
22	4,350	54	3,750	47	3,250	31	2,600	24	2,600	24	1,750	12									
25	3,850	48	3,300	41	2,850	27	2,300	22	2,300	22	1,550	11									

Increase feeds 40% to 50% for Series HP441BN.

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX

